

Monofil - Colourmatch Pre-charged Aerosol Solvent Base Product Information

Monofil Colour Match is individually produced in quality and colour. By taking care of the specific application procedures of each product, high quality surface finishes equal to the product features will be achieved. The trader is liable for the final product.



Substrate:

Fully hardened and abraded old substrates
Thoroughly dry 1K-Filler and 2K-Filler materials
It is advised to spray a sample first!



Pretreatment / Cleansing:

Pre-cleansing with silicone remover

Process: Coating Procedure



Please read the directions for use!

Colour / Grade of Gloss

Depending on the product specification.

Characteristics

Fast drying, scratch and shock resistant.
Excellent flow and surface finish.
High UV-protection, non-yellowing, lightfast, lead free
Pre-charged with an ozone-friendly mixture of solvents and propellant
Supplied with an adjustable FAN-Sprayhead

Processing Conditions

from +10°C and up to 80% relative air humidity.

VOC-regulation EC limiting value for the product (cat. B/e): 840 g/l (2007)
This product contains max. 840 g/l VOC [7.01 lbs/gal]

Drying Times:

Dust Dry
Set to touch
Full Hardness



after approx. 10 min.
after approx. 1—2 hours.
after approx. 12 hours.

Directions for use:

All substrates must be clean, dry and free from grease. Shake can vigorously for approx. 3 mins. prior to use. Spraying distance approx. 20 -30 cm.
Apply several thin layers, with a flash-off period of approx. 3 -5 Minutes between each coating.
After use, turn can upside down and spray until the valve is clean, this prevents the valve from clogging up.

Safety Information:

Only to be used in well ventilated areas. Keep away from sources of ignition, do not smoke, eat or drink. Keep out of the reach of children. Caution! Pressurised container.
Protect from sunlight and do not expose to temperatures exceeding 50°C.
For professional use only. Caution! Disposal only in accordance to the regulations of the environmental health authorities.

The data sheet is for information purposes only! The information given is in accordance to our knowledge up to the latest standards and is based on years of experience in the manufacture of our products. The information is non binding and without guarantee.