



Relofix

PE-Glasfaserspachtel

Product-Information

GB 1/0413

Page 1 / 1

Relofix is a 2-component glass fibre putty based on polyester resins free of asbestos. Because of its content of glass fibre splinters the product is especially suited for bridging cracks, small holes and rusted-through areas on iron, steel and glass fibre. As the product contains no soluble compounds and does not wash out, it is ideal for all marine repairs. An application on vertical surfaces is possible without problems.

| | | | | |
|------------------------------|---|-----------------|---------------------|---------------|
| Colour shade | milky yellow | | | |
| Mixing ratio | 100 : 2 | | | |
| Hardener | Härter P | | | |
| Thinners | | | | |
| Spraying viscosity 20° C | | | | |
| Application | spraying pressure | spraying nozzle | spraying operations | |
| Air / Flowjar - Spray gun | | | | |
| Airless / Airmix | | | | |
| Pot life | 4 - 5 min. | | | |
| Coat thickness / dry film | | | | |
| Curing time / Flash off time | | | | |
| Dry | recoat time | dust dry | set to touch | full hardness |
| Object Temp. 20° C | Sandable after approx. 20 min. | | | |
| Object Temp. 60° C | Sandable after approx. 10 min. | | | |
| VOC-regulation | EC limiting value for the product (cat. B/b): 250 g/l (2007) This product contains max. 0 g/l VOC [0 lbs/gal] | | | |

Application conditions :

Apply over +10° C and at max. 80% relative air humidity.

Remarks:

The substrate must be clean, dry and free of grease. Slightly sand surfaces! Remove old layers of paint or primer, which are not adhesive or fully dry. Do not apply on thermoplastic or acid-containing coats (eg. Washprimer). Mix well Relofix and Härter P.

All products should be disposed of in relation to the regulations of the environmental health authorities. Protect your environment.

This data sheet is for information purpose only! To our knowledge the data provided complies with the latest standard and is based on years of experience in the manufacture of our products. However the data is not binding and without warranty. Please follow recommendations stated on the relevant safety data sheet and precautions stated on the product label. We reserve our right to make additions, deletions, or modifications to the information at any time without prior notification.